

ExxonMobil™ LLDPE LL 8460 Series

Linear Low Density Polyethylene Resin

Product Description

ExxonMobil™ LLDPE LL 8460 is a linear low density hexene copolymer designed to offer excellent ESCR and toughness. This resin is ideally suited for applications that require the optimum balance of processability, stiffness and low temperature toughness.

General

Availability ¹	<ul style="list-style-type: none"> Latin America North America
Additive	<ul style="list-style-type: none"> LL 8460.29: Long Term UV-20 Stabilizer: Yes LLP8460.29: Long Term UV-20 Stabilizer: Yes
Applications	<ul style="list-style-type: none"> Agricultural Tanks Chemical Storage Tanks Large Size Playground Equipment Pallets Potable Water Tanks Septic Tanks
Form(s)	<ul style="list-style-type: none"> Pellets Powder
Revision Date	<ul style="list-style-type: none"> 09/29/2022

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.938 g/cm ³	0.938 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.3 g/10 min	3.3 g/10 min	ASTM D1238 (mod)

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	129 °F	54 °C	ASTM D648
Deflection Temperature Under Load (DTUL) at 264psi - Unannealed	99 °F	37 °C	ASTM D648
Peak Melting Temperature	260 °F	127 °C	ExxonMobil Method

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (50 mm/min)	2600 psi	18 MPa	ASTM D638
Elongation at Yield (2.0 in/min (50 mm/min))	10 %	10 %	ASTM D638
Flexural Modulus - 1% Secant	99000 psi	680 MPa	ASTM D790B
Environmental Stress-Crack Resistance			ASTM D1693A
10% Igepal, F50	60 hr	60 hr	
100% Igepal, F50	> 1000 hr	> 1000 hr	

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Impact Strength			ARM
-40°F (-40°C), 0.125 in (3.18 mm)	39 ft·lb	53 J	
-40°F (-40°C), 0.250 in (6.35 mm)	114 ft·lb	154 J	

Additional Information

All physical properties were measured on 3 mm. rotomolded samples except for ESCR, which was measured on compression molded samples.

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LLDPE LL 8460 Series
Linear Low Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2023 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com