

# ExxonMobil™ LDPE EVA Copolymers LD 364HE

## Low Density Polyethylene Resin

### Product Description

LD 364HE is an LDPE, offering a good combination of mechanical, optical and sealing properties.

### General

Availability <sup>1</sup>	▪ Africa & Middle East	▪ Europe	
Additive	▪ Antiblock: 1500 ppm	▪ Slip: 550 ppm	▪ Thermal Stabilizer: Yes
Applications	▪ Co-Extrusion Films ▪ Foams ▪ Form Fill And Seal Packaging	▪ Freezer Film ▪ High Clarity Film ▪ Lamination Film	▪ Poultry Bag ▪ Rice Bags
Revision Date	▪ 01/01/2017		

### Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.928 g/cm <sup>3</sup>	0.928 g/cm <sup>3</sup>	ASTM D1505
Melt Index (190°C/2.16 kg)	0.60 g/10 min	0.60 g/10 min	ASTM D1238
Vinyl Acetate Content	5.0 wt%	5.0 wt%	ExxonMobil Method
Peak Melting Temperature	219 °F	104 °C	ExxonMobil Method

### Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	3800 psi	26 MPa	ASTM D882
Tensile Strength at Break TD	3400 psi	24 MPa	ASTM D882
Elongation at Break MD	170 %	170 %	ASTM D882
Elongation at Break TD	540 %	540 %	ASTM D882
Secant Modulus MD - 1% Secant	25000 psi	170 MPa	ASTM D882
Secant Modulus TD - 1% Secant	29000 psi	200 MPa	ASTM D882
Dart Drop Impact	360 g	360 g	ASTM D1709A
Elmendorf Tear Strength MD	180 g	180 g	ASTM D1922
Elmendorf Tear Strength TD	110 g	110 g	ASTM D1922

### Optical Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	52	52	ASTM D2457
Haze	9.8 %	9.8 %	ASTM D1003

### Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

### Processing Statement

The test specimen were prepared on LD 364HE, 50µm (1.97mil) thick film, using a 200 mm (7.9 in) die, die gap of 1.0 mm (39.4 mil), Blow-Up Ratio 2.5 and temperature profile of 180 - 190°C (356- 374°F).

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LDPE EVA Copolymers LD 364HE  
Low Density Polyethylene Resin

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2022 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)