

SpectraSyn™ MaX 3.5

Advanced Polyalphaolefin (PAO) Fluid

Product Description

SpectraSyn™ MaX 3.5 is the next generation Polyalphaolefin (PAO) that leverages a unique structure to achieve an exceptional low viscosity, low volatility balance. SpectraSyn™ MaX 3.5 PAO offers improved oxidative stability, enhanced lubricity and traction, excellent low-temperature properties and improved flashpoint versus conventional PAO. SpectraSyn™ MaX 3.5 PAO delivers step-out performance for fuel efficiency improvements as the primary basestock for synthetic lubricants for engine oil and driveline applications. SpectraSyn™ MaX 3.5 PAO also offers improved energy efficiency and thermal management benefits for electric vehicle driveline and e-motor applications and more broadly, enables improved energy efficiency in industrial applications. This product is registered on the LuSC list and can be used to formulate EcoLabel, and other Environmentally Acceptable Lubricants.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Revision Date	03/10/2021		

Basics	Typical Value (English)	Typical Value (SI)	Test Based On
Specific Gravity ² (60.1°F (15.6°C))	0.817	0.817	ASTM D4052
Appearance (0°F (-18°C))	Bright & Clear	Bright & Clear	Visual
Color	< 0.5	< 0.5	ASTM D1500
Kinematic Viscosity ²			ASTM D445
212°F (100°C)	3.5 cSt	3.5 mm ² /s	
104°F (40°C)	14.3 cSt	14.3 mm ² /s	
-40°F (-40°C)	1670 cSt	1670 mm ² /s	
Viscosity Index	129	129	ASTM D2270
Pour Point	< -108 °F	< -78 °C	ASTM D5950/D97
Flash Point, COC	453 °F	234 °C	ASTM D92
Noack Volatility ²	< 11.6 wt%	< 11.6 wt%	ASTM D5800/DIN 51581
Water	< 9 ppm	< 9 ppm	ASTM D6304
Total Acid Number	< 0.0200 mg K/g	< 0.0200 mg K/g	ASTM D974 (mod)

Flow	Typical Value (English)	Typical Value (SI)	Test Based On
Apparent Viscosity by Mini-Rotary Viscometer ²			ASTM D4684
-40°F (-40°C)	1317 cP	1317 cP	
Brookfield Viscosity ² (-40°F (-40°C))	1255 cP	1255 cP	ASTM D2983
Cold Cranking Simulator ²			ASTM D5293
-22°F (-30°C)	518 cP	518 cP	
-31°F (-35°C)	790 cP	790 cP	

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Density Correction Factor ³	6.73E-4 (g/cm ³)/°C	6.73E-4 (g/cm ³)/°C	ASTM D1250
Fire Point, COC ²	489 °F	254 °C	ASTM D92
Evaporation Loss ² (401°F (205°C), 6.5 hr)	4.0 wt%	4.0 wt%	ASTM D972 (mod)
Vapor Pressure ³ (302°F (150°C))	0.2 mm Hg	0.2 mm Hg	ASTM D2879

Performance	Typical Value (English)	Typical Value (SI)	Test Based On
Dielectric Constant ³ (77°F (25°C))	2.08	2.08	ASTM D924
Dielectric Strength ³	34.0 kV	34.0 kV	ASTM D877
High-Temp. High-Shear Viscosity ²	1.29 cP	1.29 cP	ASTM D5481

Solubility	Typical Value (English)	Typical Value (SI)	Test Based On
Aniline Point ³	244.9 °F	118.3 °C	ASTM D611

SpectraSyn™ MaX 3.5
Advanced Polyalphaolefin (PAO) Fluid

Additional Information

Technical White Mineral Oil, 21 CFR 178.3620(b)

National Sanitation Foundation (NSF) White book, category code H1, Lubricants with incidental food contact

Legal Statement

For detailed Product Stewardship information, please contact Customer Service.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Single sample or two sample average determinations

³ Calculated

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com